

| | | | | | | | | |
|-----------------|---------------|--------|------------|----------|----------|--------|--------|--------|
| Name | Class | | Date | Time | Duration | | | |
| 1503LH-SC-ST058 | o MiningLE-FP | | 17/01/2023 | 10:36:30 | 10 s | | | |
| Element | Mg % | Al % | Si % | P % | Ca % | V % | Mn % | Fe % |
| | 16.2341 | 0.3189 | 26.0465 | 0.0446 | 6.1609 | 0.0944 | 0.0852 | 1.6770 |
| Element | Ni % | Rb % | Sr % | Zr % | Ba % | | | |
| | 0.0530 | 0.0009 | 0.0022 | 0.0022 | 0.0355 | | | |

